














GRES PORCELLANATO IMPASTO COLORATO . COLORED BODY PORCELAIN STONEWARE

www.dadoceramica.it

GRÈS CÉRAME MASSE COLORÉ . FEINSTEINZEUG MIT EINGEFAERBTEN SCHERBEN

UNI EN 14411 Bia Allegato G (ISO 13006)

Caratteristica tecnica Technical feature Caractéristique technique Technische Eigenschaft	Norma Norm Norme Norm	Valore richiesto dalle norme Required standards Valeur prescrite par les normes Normvorgabe	MANSION		
			Naturale	Outdoor	
 <p>Lunghezza e larghezza / Lenght and width Longuer et largeur / Länge und breite</p> <p>Spessore / Thickness Epaisseur / Stärke</p> <p>Rettilineità spigoli / Straightness of sides Rectitude des aretes / Kantengeradheit</p> <p>Ortogonalità / Rectangularity Orthogonalite / Rechtwinkligkeit</p> <p>Planarità / Surface flatness Planeite de surface / Ebenflächigkeit</p>	UNI EN ISO 10545-2	N ≥ 15 cm		<p>Conforme Corresponding Conforme Entsprechend</p>	
		%	(mm)		
		± 0,6 Non Rect. ± 0,3 Rect	± 2,0 Non Rect. ± 1,0 Rect		
		± 5	± 0,5		
		± 0,5 Non Rect. ± 0,3 Rect	± 1,5 Non Rect. ± 0,8 Rect		
± 0,5 Non Rect. ± 0,3 Rect	± 2,0 Non Rect. ± 1,5 Rect				
± 0,5 Non Rect. ± 0,4 Rect	± 2,0 Non Rect. ± 1,8 Rect				
 <p>Qualità della superficie Surface quality Qualités de la surface Oberflächenqualität</p>	UNI EN ISO 10545-2	<p>Il 95 % min. delle piastrelle di prova deve essere esente da difetti visibili Minimum 95% of the tested tiles must be free from visible defects 95% min. des carreaux de test ne doit pas contenir de défauts visibles Min. 95% der geprüften Fliesen dürfen keine sichtbaren Mängel aufweisen</p>		<p>Conforme Corresponding Conforme Entsprechend</p>	
 <p>Assorbimento d'acqua Water absorption Absorption d'eau Wasseraufnahme</p>	UNI EN ISO 10545-3	<p>≤ 0,5% Individual max 0,6%</p>		<p>≤ 0,5%</p>	
 <p>Sforzo di Rottura / Breaking strength Effort de rupture / Bruchkraft (≥ 7,5 mm thickness)</p> <p>Resistenza alla flessione / Modulus of Rupture Résistance à la flexion / Biegefestigkeit</p>	UNI EN ISO 10545-4	<p>S ≥ 1300 N</p>		<p>S ≥ 1300 N</p>	
		<p>R ≥ 35 N/mm²</p>		<p>R ≥ 35 N/mm²</p>	
 <p>Resistenza all'abrasione (metodo PEI) Abrasion resistance (PEI test) Résistance à l'abrasion (méthode PEI) Widerstand gegen Abrieb (nach PEI)</p>	UNI EN ISO 10545-7	<p>Segnala la classe di abrasione e i cicli superati Report abrasion class and cycles passed</p>		<p>EXTREME PEI III MID-WARM-COLD PEI IV</p>	
 <p>Resistenza al gelo Resistance to frost Résistance aux gel Frostbeständigkeit</p>	UNI EN ISO 10545-12	<p>Richiesto Required</p>		<p>Non gelivo Frost-proof Non gélifs Frostsicher</p>	
 <p>Resistenza ai prodotti chimici Resistance to chemical products Résistance aux produits chimiques Widerstand gegen Chemikalien</p>	UNI EN ISO 10545-13	<p>Resistenza a basse concentrazioni di acidi e alcali Resistance to low concentrations of acids and alkalis Secondo la classificazione indicata dal fabbricante Manufacturer is to state classification</p>		<p>LA</p>	
		<p>Resistenza ad alte concentrazioni di acidi e alcali Resistance to high concentrations of acids and alkalis Metodo di prova disponibile Test method available</p>		<p>HA</p>	
		<p>Resistenza ai prodotti chimici di uso domestico ed agli additivi per piscina Resistance to household chemicals and swimming pool salt Classe minima B Minimum class B</p>		<p>A</p>	
 <p>Resistenza alle macchie Staining resistance Résistance aux taches Widerstand gegen Fleckenbildung</p>	UNI EN ISO 10545-14	<p>Min. 3</p>		<p>Conforme Corresponding Conforme Entsprechend</p>	
 <p>Resistenza agli sbalzi termici Thermal shock resistance Résistance aux écarts de température Temperaturwechselbeständigkeit</p>	UNI EN ISO 10545-9	<p>Metodo di prova disponibile Test method available</p>		<p>Resiste Resistant Résiste Widerstandsfähig</p>	
Caratteristiche accessorie / Additional features					
 <p>Stabilità dei colori Colours stability Stabilité des couleurs Farbbeständigkeit</p>	DIN 51094	<p>Colorazione Stabile Stable coloring</p>		<p>Conforme Corresponding Conforme Entsprechend</p>	
Caratteristiche di sicurezza / Safety characteristics					
 <p>Resistenza allo scivolamento** Slip resistance Résistance au glissement Rutschemmende Eigenschaft</p>	METODO B.C.R.A.	<p>μ > 0,40</p>		<p>Conforme Corresponding Conforme Entsprechend</p>	
	DIN EN 16165	<p>ANNEX A Test della rampa a piedi nudi / Classe dichiarata Barefoot ramp test / Declared Class Méthode de la rampe pieds nus / Classe déclarée Methode der schiefen Ebene, barfuß / Angegebene Klasse</p>		<p>A+B</p>	<p>A+B+C</p>
		<p>ANNEX B Test della rampa a piedi calzati / Classe dichiarata Shod ramp test / Declared Class Rampe avec chaussures / Classe déclarée Methode der schiefe Ebene, mit Schuhwerk / Angegebene Klasse</p>		<p>R10</p>	<p>R11</p>
DCOF (ANSI A 326.3)	<p>≥ 0,42</p>		<p>Conforme Corresponding Conforme Entsprechend</p>		