




Dado Ceramica S.r.l.

Via Sicilia 21 - 40017 - San Matteo della Decima (BO) - Italy











Telefono +39 051 6819611 - Telefax +39 051 6819650

info@dadoceramica.it - Follow us   

RIVESTIMENTI IN PASTA BIANCA . WHITE-BODY WALL TILE
REVÊTEMENTS EN PÂTE BLANCHE . WEISSSCHERBIGE WANDFLIESEN

www.dadoceramica.it

UNI EN 14411 BIII Allegato L (ISO 13006)

Caratteristica tecnica Technical feature Caractéristique technique Technische Eigenschaft	Norma Norm Norme Norm	Valore richiesto dalle norme Required standards Valeur prescrite par les normes Normvorgabe	RIVESTIMENTI WALL TILES	
 <p>Lunghezza e larghezza / Length and width Longuer et largeur / Länge und breite</p> <p>Spessore / Thickness Epaisseur / Stärke</p> <p>Rettilineità spigoli / Straightness of sides Rectitude des arêtes / Kantengeradheit</p> <p>Ortogonalità / Rectangularity Orthogonalité / Rechtwinkligkeit</p> <p>Planarità / Surface flatness Planeité de surface / Ebenflächigkeit</p>	UNI EN ISO 10545-2	N ≥ 15 cm		
		%	(mm)	
		± 0,6 Non Rect. ± 0,3 Rect	± 2,0 Non Rect. ± 1,0 Rect	
		± 10	± 0,5	
		± 0,5 Non Rect. ± 0,3 Rect	± 1,5 Non Rect. ± 0,8 Rect	
± 0,5 Non Rect. ± 0,3 Rect	± 2,0 Non Rect. ± 1,5 Rect	± 0,5 Non Rect. ± 0,4 Rect	± 2,0 Non Rect. ± 1,8 Rect	Conforme Corresponding Conforme Entsprechend
 <p>Qualità della superficie Surface quality Qualités de la surface Oberflächenqualität</p>	UNI EN ISO 10545-2	<p>Il 95 % min. delle piastrelle di prova deve essere esente da difetti visibili Minimum 95% of the tested tiles must be free from visible defects 95% min. des carreaux de test ne doit pas contenir de défauts visibles Min. 95% der geprüften Fliesen dürfen keine sichtbaren Mängel aufweisen</p>		Conforme Corresponding Conforme Entsprechend
 <p>Assorbimento d'acqua Water absorption Absorption d'eau Wasseraufnahme</p>	UNI EN ISO 10545-3	> 10 %		Conforme Corresponding Conforme Entsprechend
 <p>Sforzo di Rottura / Breaking strength Effort de rupture / Bruchkraft</p>	UNI EN ISO 10545-4	Spessore / Thickness ≥ 7,5 Non meno di / Not less than 600 N		> 600 N
		Spessore / Thickness < 7,5 Non meno di / Not less than 200 N		> 200 N
 <p>Resistenza alla flessione / Modulus of Rupture Résistance à la flexion / Biegefestigkeit</p>	UNI EN ISO 10545-4	Spessore / Thickness ≥ 7,5 Minimo / Minimum 12 N/mm²		> 12 N/mm ²
		Spessore / Thickness < 7,5 Minimo / Minimum 15 N/mm²		> 15 N/mm ²
 <p>Resistenza agli sbalzi termici Thermal shock resistance Resistance aux écarts de température Temperaturwechselbeständigkeit</p>	UNI EN ISO 10545-9	Metodo di prova disponibile Test method available		Resiste Resistant Résiste Widerstandsfähig
 <p>Resistenza al cavillo Crazing resistance Résistance au tressillage Haarißbeständigkeit</p>	UNI EN ISO 10545-11	Richiesta Requested Demandée Gefragt		Conforme Corresponding Conforme Entsprechend
 <p>Resistenza al gelo Resistance to frost Resistance aux gel Frostbeständigkeit</p>	UNI EN ISO 10545-12	Richiesto Required		Non gelivo Frost-proof Non gélifs Frostsicher
 <p>Resistenza agli acidi Chemical resistance Résistance à l'attaque chimique Beständigkeit gegen Chemikalien</p>	UNI EN ISO 10545-13	<p>Resistenza ai prodotti chimici di uso domestico ed agli additivi per piscina Resistance to household chemicals and swimming pool salt Classe minima B Minimum class B</p>		A
 <p>Resistenza alle macchie Staining resistance Résistance aux taches Widerstand gegen Fleckenbildung</p>	UNI EN ISO 10545-14	Classe 3 Class 3 Classe 3 Klasse 3		Conforme Corresponding Conforme Entsprechend